

## CLAIMS

1. A transparent elastomer composition comprising an elastomer and fluorine-containing resin fine particles which are finely  
5 dispersed in the elastomer.

2. A composition comprising a transparent elastomer composition which comprises an elastomer and fluorine-containing resin fine particles which are finely dispersed in the elastomer and  
10 further containing a filler.

3. The composition of Claim 1 or 2, wherein the elastomer is a fluorine-containing elastomer.

15 4. The composition of any of Claims 1 to 3, wherein the composition contains a crosslinking agent.

5. The composition of any of Claims 1 to 4, wherein the transparent elastomer composition has a haze value of not more than  
20 50 %.

6. A process for preparing the transparent elastomer composition of Claim 1, which comprises mixing an emulsion of elastomer particles and an emulsion of fluorine-containing resin fine  
25 particles, and co-coagulating the mixture.

7. The process of Claim 6, wherein the emulsion of fluorine-containing resin fine particles is an emulsion of fluorine-containing  
30 resin fine particles having an average particle size of from 20 to 150 nm.

8. An elastomeric molded article which is obtained by vulcanizing and molding a transparent elastomer composition comprising an elastomer and  
5 fluorine-containing resin fine particles which are finely dispersed in the elastomer, said fluorine-containing resin fine particles having an average particle size of from 20 to 100 nm.

9. The elastomeric molded article of Claim 8, which is transparent.

10  
10. The elastomeric molded article of Claim 9, which has a haze value of not more than 50%.

11. An elastomeric molded article which is obtained by vulcanizing  
15 and molding a composition comprising a transparent elastomer composition which comprises an elastomer and fluorine-containing resin fine particles which are finely dispersed in the elastomer and further containing a filler, said fluorine-containing resin fine particles having an average particle size of from 20  
to 100 nm.

20  
12. The elastomeric molded article of Claims 11, which is transparent.

13. The elastomeric molded article of Claim 12, which has a haze  
25 value of not more than 50%.